



# ABS-PRO-X FAST SET MEDIUM YELLOW CEMENT TECHNICAL SPECIFICATION

Job Name _____	Item # _____
Location _____	
Engineer _____	Contractor _____
PO # _____	Tag _____
Representative _____	

## SPECIFICATIONS

- Medium-bodied yellow cement for use on all schedules and classes of ABS pipe and fittings up to 6" diameter with interference fit.
- Lo-V.O.C. Solvent Cement meets California South Coast Air Quality Management District (SCAQMD) 1168/316A or BAAQMD Method 40 and various environmental requirements.

## APPLICATION / USES

- For all non-pressure applications.

## PROPERTIES

VOC
Maximum VOC per SCAQMD 1168/316A or BAAQMD Method 40: 325 g/L

CHEMICAL PROPERTIES	
Appearance	Yellow Liquid
Viscosity	Min. 500° cps @ 73° F ± 2° F
Density	7.23 ± 0.2 lbs/gallon
Shelf Life	3 Years from Mfg. Date

SET TIME / CURE TIME	
30° F to 50° F	4 – 5 minutes
50° F to 70° F	2 – 3 minutes
70° F to 90° F	1 – 2 minutes



CSA B181.1, ASTM D2235, NSF Standard 14 for DWV and Sewer, IAPMO Listed

PRODUCT NUMBER	SIZE	DESCRIPTION	CTN. QTY
ABS250-X	8 oz.	ABS Medium Yellow Cement	24
ABS500-X	16 oz.	ABS Medium Yellow Cement	24
ABS1L-X	32 oz.	ABS Medium Yellow Cement	12
ABS4L-X	Gallon	ABS Medium Yellow Cement	6

§ Compliant with LEED Requirements. Solvent cements may be specified under the LEED v4 EQ for Low-Emitting Materials to obtain points



# ABS-PRO-X FAST SET MEDIUM YELLOW CEMENT TECHNICAL SPECIFICATION

## DIRECTIONS

Store and use at temperatures between 40°F and 110°F.

- At temperatures outside of this range, special care must be taken to make good joints.

Stir or shake before using; if jelly-like, don't use. Do not thin

1. Pipe ends must be cut square, deburred and chamfered.
2. Check interference fit of pipe and fitting. Pipe should easily go 1/3 to 2/3 of the way into the fitting. If pipe bottoms inside the fitting hub without interference, proper fusion may not be achieved.
3. Use a suitable applicator that is at least 1/2 the size of the pipe diameter. For larger size pipe systems use a natural bristle brush or roller.
4. Clean pipe and fitting with a pipe cleaner or rag.
5. Apply liberal coat of cement on pipe to the depth of the fitting hub, leave no uncoated surface. Apply a thin coat of cement to inside of fitting, avoid puddling of cement. Puddling can cause weakening and premature failure of pipe or fitting. Apply a second coat of cement to the pipe.
6. Assemble parts QUICKLY. Cement must be fluid.
7. Push pipe FULLY into fitting using a 1/4 turning motion until pipe bottoms.
8. Hold pipe and fitting together for 30 seconds to prevent pipe push-out - longer at low temperatures. Wipe off excess.
9. Allow 15 minutes for good handling strength.
10. Allow correct cure times to pass before the plumbing system is tested.
  - Cure times are calculated based on pipe materials, pipe size, pressure and temperature of fluids passing through the pipes, humidity, ambient temperatures and the cement used for the application.
  - If you are unsure of the correct cure times for your application, please reach out to our customer service department for assistance (800) 321-9532

TESTING A PLUMBING SYSTEM WITH AIR, REGARDLESS OF THE TYPE OF SOLVENT CEMENT USED, IS DANGEROUS AND NOT RECOMMENDED..

## PRECAUTIONS

Read all information carefully before using this product.

**DANGER!: HIGHLY FLAMMABLE LIQUID AND VAPOR • CAUSES SERIOUS EYE IRRITATION • MAY BE FATAL IF SWALLOWED AND ENTERS AIRWAYS • MAY CAUSE DROWSINESS OR DIZZINESS • MAY CAUSE RESPIRATORY IRRITATION • READ ENTIRE LABEL CAREFULLY. KEEP OUT OF REACH OF CHILDREN.**

**Prevention:** Keep away from heat, sparks, open flames or hot surfaces. No smoking. Use only outdoors or in a well-ventilated area. Keep container tightly closed. Ground container and receiving equipment. Use explosion-proof electrical, ventilating, lighting equipment. Use only non-sparking tools. Take precautionary measures against static discharge. Avoid breathing mist or vapor. Wash thoroughly after handling. Do not eat, drink or smoke when using this product. Wear protective gloves, protective clothing, eye-protection, and face protection. Wear a NIOSH approved respirator for organic solvents. Vapors may accumulate in low places and may ignite explosively. Repeated exposure to solvents may cause skin dryness or cracking.

**Response:** Specific treatment (see below).

**EMERGENCY/FIRST AID: CALL 1-877-740-5015 FOR INSTRUCTIONS.**

**IF SWALLOWED:** Immediately call a POISON CENTER/doctor. Do NOT induce vomiting. Rinse mouth. This product may be aspirated into the lungs and cause chemical pneumonitis, a potentially fatal condition. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists, get medical attention. **IF ON SKIN:** Rinse skin with water/shower. Take off immediately all contaminated clothing. **IF INHALED:** Remove person to fresh air and keep comfortable for breathing. Call POISON CENTER/doctor if you feel unwell. If medical advice is needed, have product container or label at hand.

**FIRE:** Use dry chemical, foam, or carbon dioxide extinguisher. Water spray may be applied to reduce potential vapors or for cooling. Burning liquid extinguished with water will float and may re-ignite on surface of water.

**SPILLS:** Remove all sources of ignition and ventilate area. Personnel cleaning up the spill should wear appropriate personal protective equipment, including respirators if vapor concentrations are high. Soak up spill with absorbent material. Put absorbent material in covered, labeled metal containers. Dispose of contents/container in accordance with local regulations. Store in a well-ventilated space. Store locked up.

§ Compliant with LEED Requirements. Solvent cements may be specified under the LEED v4 EQ for Low-Emitting Materials to obtain points