

TURF-TITE™

HOT BLUE PVC CEMENT

MAXIMIZE YOUR PRODUCTIV WITH TURF-TITE HOT BLUE CEMENT!

If you assemble irrigation and sprinkler systems, count on Turf-Tite to help you do the job right the first time.

FAST

- Turf-Tite cement sets up fast
- Sets up in just 1–2 minutes (see chart)

30°F to 50°F	50°F to 70°F	70°F to 100°F
4–5 Minutes	3-4 Minutes	1–2 Minutes

Bond strengths in excess of 250 psi in 10 minutes under lab conditions



EASY

2446S Shown

- Versatile cement used in many applications
- Recommended for use on all schedules and classes of flexible and rigid PVC pipe and fittings up to 6" with interference fit
- No primer needed on non-pressure DWV up to 4" where local codes permit

System may be hydrostatically tested up to 75 PSI after 15 minutes and up to 180 PSI after 30 minutes.*

* At temperatures above 60°F and up to 2" pipe diameter.

Product Number	Size	Description	Carton Qty	
2466S	4 oz.	Turf-Tite PVC Medium "Hot" Blue Cement	24	
2456S	8 oz.	Turf-Tite PVC Medium "Hot" Blue Cement	24	
2446S	16 oz.	Turf-Tite PVC Medium "Hot" Blue Cement	24	
2436S	32 oz.	Turf-Tite PVC Medium "Hot" Blue Cement	12	
2424	Gallon	Turf-Tite PVC Medium "Hot" Blue Cement	6	
California Compliant: SCAQMD Rule 1168-23				
2466S	4 oz.	Turf-Tite PVC Medium "Hot" Blue Cement - Rule 1168-23	24	
2456S	8 oz.	Turf-Tite PVC Medium "Hot" Blue Cement - Rule 1168-23	24	
2446S	16 oz.	Turf-Tite PVC Medium "Hot" Blue Cement - Rule 1168-23	24	
2436S	32 oz.	Turf-Tite PVC Medium "Hot" Blue Cement - Rule 1168-23	12	
2424	Gallon	Turf-Tite PVC Medium "Hot" Blue Cement - Rule 1168-23	6	

























